

# Technical Data Sheet



## Core Board for Tissue Cores

Rev.: January 2021

Parameter		Unit	2-ply	2-ply	2-ply	2-ply	2-ply	2-ply	1-ply	1-ply	
<b>Basis Weight</b>		g/m <sup>2</sup>	<b>140</b>	<b>150</b>	<b>160</b>	<b>170</b>	<b>180</b>	<b>210</b>	<b>280</b>	<b>320</b>	DIN EN ISO 536
<b>Moisture</b>		%	<b>5,5</b>	<b>5,5</b>	<b>5,5</b>	<b>5,5</b>	<b>5,5</b>	<b>5,5</b>	<b>6,5</b>	<b>6,5</b>	DIN EN 20287
<b>Tensile Strength</b>	md	kN/m	<b>85</b>	<b>90</b>	<b>100</b>	<b>105</b>	<b>110</b>	<b>120</b>	<b>165</b>	<b>175</b>	DIN EN ISO 1924-2
<b>Shade</b>			<b>grey</b>	<b>grey</b>	<b>grey</b>	<b>grey</b>	<b>grey</b>	<b>grey</b>	<b>grey</b>	<b>grey</b>	

Basis Weight ± 3 %

Moisture ± 1 %

Tensile Strength ± 10 %

Roughness: According to customer requirements

Quality measured at norm climate 23°C / 50% rel. humidity