

Optik

WOODFREE / PAPEL BOND

Test Físico	Unidad	Tolerancia											Metodo
Grammage	g/m ²	+/- 3%	55	58	65	68	74	78	88	98	110		GB/T 451.2
thickness	µm	+/- 4%	74	76	85	88	97	101	115	127	147		GB/T 451.3
Brightness	% ISO	+/- 1	98	98	98	98	98	98	98	98	98		GB/T 7979
Opacity	%	min	87	89	89	92	92	92	92	95	95		GB/T 1543
Smoothness	S	min	32	32	32	32	32	32	32	32	32		GB/T 456
Breaking Length	MD	km	min	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5		GB/T 12914
	CD		min	2	2	2	2	2	2	2	2	2	
Moisture	%	+/- 1	6	6	6	6	6	6	6	6	6		GB/T 462
COBB	g/m ²	+/- 10	30	30	30	30	30	30	30	30	30		GB/T 1540

Test condition: ISO Temperature: 23±1°C Humidity: 50±2%RH

