


Physical Test		Test Method	*Basic-Weight*(g/m ²)	
			75	80
Kind of Test		Reference		
Grammage, g/m ²		T410 om-98	75 - 76	80 - 81
Thickness, μm		T411 om-97	≥ 100	≥ 107
Smoothness, sec/10ml		T479 om-91	≥ 22	≥ 22
Brightness, %ISO (C/2°)		ISO 2470-1999	96 \pm 1	96 \pm 1
CIE Whiteness (D65/10°)		ISO 11475-1999	157.5 \pm 2.5	157.5 \pm 2.5
Opacity, %		ISO 2471-1999	92 \pm 1	95 \pm 1
Stiffness, mN.m	MD	T535 om-96	≥ 0.36	≥ 0.40
	CD		≥ 0.16	≥ 0.18
Wax Pick, °A		T459 om-93	≥ 14	≥ 14
Coefficient of Friction Static		T548 pm-90	0.50 - 0.65	0.50 - 0.65
Moisture, %		T412 om-94	4.5 \pm 0.5	4.5 \pm 0.5

Quality Assurance



CHRESNO JUNIARSO

02-Oct-10