

Product information sheet

Sappi ECO Offset / WEB ECO Offset

Uncoated fine paper available in reels and sheets

Technical specifications

PARAMETER	STANDARD	UNIT											
BASIS WEIGHT	ISO 536	g/m²	140	150	160	170	180	200	228	240	250	280	300
BRIGHTNESS (illuminant D65/10°)	ISO 2470-2	%	103	103	103	103	103	103	103	103	103	103	103
CIE WHITENESS (D65/10°)	ISO 11475	%	142	142	142	142	142	142	142	142	142	142	142
OPACITY	ISO 2471	%	97	97	97,5	97,5	98	98,5	98,5	99	99	99,5	100
ROUGHNESS BENDTSEN	ISO 8791-2	ml/min	<450	<450	<450	<450	<450	<450	<450	<450	<450	<450	<450
THICKNESS	ISO 534	µm	165	177	189	201	212	236	269	283	295	330	354
SPEC. VOLUME	ISO 534	cm ³ /g	1,18	1,18	1,18	1,18	1,18	1,18	1,18	1,18	1,18	1,18	1,18
RELATIVE HUMIDITY (23°C)	TAPPI 502	%	50	50	50	50	50	50	50	50	50	50	50
PH VALUE	ISO 6588	-	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7

MILL CERTIFICATION

PRODUCT CERTIFICATION

EMAS	ISO 14001	ISO 9001	OHSAS 18001	PEFC™ CoC	FSC® CoC	TCF/ ECF	PEFC™ credit material	FSC® Mix	Food contact	Toy safety
✓	✓	✓	✓	✓	✓	✓	✓	✓		

FSC® & PEFC™ may have limited availability, please check with your local sales office.
To learn more about all of these certifications and to receive copies please contact your local sales office.

Target production values

Regional variations in specifications may apply; please contact your local Sales office for more information.

Updated: March 2016

