

EN

Coated Paper 2 Sides Gloss

Property			Unit	Tolerance																	
Substance	ISO 536	TAPPI T410	gsm	± 4%	80	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380	
Thickness	ISO 534	TAPPI T411	µm	± 4%	63	69	78	89	91	95	100	110	125	148	171	190	205	232	285	310	
Brightness R457 D65	ISO 2470-2	-	%	± 2	94,4	95,2	95,2	95,2	95,2	95,2	95,2	95,2	95,2	95,2	95,2	95,2	95,2	95,2	95,2	95,2	95,2
Whiteness CIE D65/10°	ISO 11475	-	-	± 3	119	119	119	119	119	119	119	119	119	119	119	119	119	119	119	119	119
Opacity	ISO 2471	TAPPI T519	%	-2.0	89,0	91,0	92,5	93,5	94,5	95,0	95,5	96,5	97,0	-	-	-	-	-	-	-	-
Paper Gloss	ISO 8254-1	TAPPI 480	%	±5	65	66	67	68	72	72	72	73	74	74	74	74	74	74	74	74	74
Smoothness Bekk	ISO 5627	TAPPI T479	s	±30%	1400	1400	1100	950	1100	1000	1000	1000	850	600	550	500	400	350	250	200	
Relative Humidity	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Last updated: **01-01-17**
- Values are subject to change without notice.

ES

Estucado 2 Caras Brillante

Propiedad			Unidades	Tolerancia																
Gramaje	ISO 536	TAPPI T410	gsm	± 4%	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380	
Calibre	ISO 534	TAPPI T411	µm	± 4%	69	78	89	91	95	100	110	125	148	171	190	205	232	285	310	
Brightness R457 D65	ISO 2470-2	-	%	± 2	96	96	96	96	96	96	96	96	96	96	96	96	96	96	96	96
Blancura CIE D65/10°	ISO 11475	-	-	± 3	119	119	119	119	119	119	119	119	119	119	119	119	119	119	119	119
Opacidad	ISO 2471	TAPPI T519	%	-2.0	91,0	92,5	93,5	94,5	95,0	95,5	96,5	97,0	-	-	-	-	-	-	-	-
Brillo de papel	ISO 8254-1	TAPPI 480	%	±5	66,0	67,0	68,0	72,0	72,0	72,0	73,0	74,0	74	74	74	74	74	74	74	74
Rugosidad Parker	ISO 5627	TAPPI T479	s	±30%	1400	1100	950	1100	1000	1000	1000	850	600	550	500	400	350	250	200	
Humedad relativa	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Última actualización: **01-01-17**
- Los valores están sujetos a cambio sin aviso previo.

