



## DATA SHEET

### PRODUCT:

Face Material: **OPP TC REV  
WHITE MATT 70**

Adhesive: **PF2**

Backing Paper: **CB62**

ARCONVERT SpA  
Sede legale e amministrativa:  
Strada del Linfano, 12  
38062 Arco (TN), Italy  
Tel. +39 0464.584444 r.a.  
Fax Comm. +39 0464.532024  
Fax Amm. +39 0464.584490  
Fax Acq. +39 0464.531291

arconvert.com  
Cap. Soc. €4.000.000 i.v.  
Codice Fiscale e Registro  
Imprese n. 01077840682  
Partita IVA e VAT Code IT  
n. 01192310223  
N. Mecc. TN 007450  
N. REA TN 122101

**Face Material: OPP TC REV WHITE MATT 70**

Description: White, opaque TOP-COATED polypropylene film.

Application: General all purpose plastic film. Completely recyclable together with compatible plastic products such as polyethylene or polypropylene containers. Resistant to weather and most chemical agents. Top Coating ensures excellent printing results with all conventional printing systems. Suited to hot stamping print techniques (information on compatible inks and printing techniques available on request).

Technical Data	Grammage	Caliper	Brightness	Opacity	Glaze	Tensile-strength h MD-CD	Elongation at break MD-CD
	g/m2	micron	%	%	%	Kg/15 mm	%
	48	70	90		9		165-50

**Adhesive: PF2**

Description: Acrylic adhesive in water emulsion.

Application: Adhesive for plastic films. Good adhesion on apolar surfaces. High resistance to UV rays. High transparency makes this product ideal for "no-label-look" labels. Approved for indirect food contacts and corresponding to UNI-EN 71/3 "toys security" norms.

Technical Data	Tack	Cohesion (min)	Application Temperature (min)	Service Temperature (min)	Service Temperature (max)
	g/25 mm	hours	° C	° C	° C
	900	15	+ 10	-10	+ 100

**Backing paper: CB62**

Description: Super calandered glassine paper, siliconised on one side.  
Colour: WHITE. There may be slight variations in tone.

Application: Backing paper designed for automatic label generation. Ideal for photocells dispensing system.

Technical Data	Grammage	Caliper	Opacity	Trasparenza	Tensile-strength MC-CD	Elongation at break MD-CD
	g/m2	micron	%	%	N/15mm	%
	62	56		51	80-32	

Date  
09/03/2001

Report  
n° NIN 334

Revision  
2

Q.C. Manager  
Ing. Sabrina Leoni

All the information and descriptions regarding Arconvert products are based research and are considered reliable, but do not constitute a warranty.

Given the extent and constant development of fields of application for Arconvert self-adhesive products, the user must carefully check the suitability of the product for each specific application, bearing all the risks involved. No salesman, agent or representative is authorised to issue guarantees or information other than those contained in this guide which replaces previous editions and information contained herein is subject to change without notice.